



Jiaxing Selected Technology Co., Ltd.

PRODUCT: AERO AIR DOME TYPE2

Item	Test method	Unit	Test value
Support Cloth	DIN ISO 2076		100%PES
Total Weight	DIN EN ISO 2286-2	g/m2	950
Composition Fabric	DIN EN ISO 2286-2	g/m2	260
Composition Coating		g/m2	690
Width	DIN EN ISO 2286-1	cm	300
Thickness	DIN EN ISO 2286-2	mm	0.76
Tensile strength Warp	DIN 53354	N/5cm	4000
Tensile strength Weft	DIN 53354	N/5cm	3600
Tear strength Warp	DIN 53363	N	500
Tear strength Weft	DIN 53363	N	500
Adhesion Strength	DIN 53357	N/5cm	150
Temperature Resistance	BS 3424 Method 10		-30℃ /+70℃
Flame Retardant	B1,B-s2,d0		
Lacquering (optional)	PVDF, Acrylic		
Application	AIR DOME		

These indicated technical data are based on average results. actual data 's tolerance +-5%.Due to production procedures slight deviations can occur.All technical data are in accordance with the present standard of knowledge and give product information without legal binding.All data apply to new products

Company : Jiaxing Selected Technology Co., Ltd.

Ad : No.1, Fenghuang dongyuan,Dingqiao,Haining,Zhejiang.China. 314413

Email: admin@selectedfabric.com

Website: www.selectedfabric.com