



ZHEJIANG JINDA MEMBRANE TECHNOLOGY CO.,LTD.

PRODUCT: AERO BLACKOUT BLA850

Item	Test method	Unit	Test value
Support Cloth	DIN ISO 2076		100%PES
Total Weight	DIN EN ISO	g/m ²	850
Composition Fabric	DIN EN ISO	g/m ²	200
Composition Coating		g/m ²	650
Width	DIN EN ISO	cm	250-300
Tensile strength Warp	DIN 53354	N/5cm	3200
Tensile strength Weft	DIN 53354	N/5cm	3000
Tear strength Warp	DIN 53363	N	300
Tear strength Weft	DIN 53363	N	260
Adhesion Strength	DIN 53357	N/5cm	120
UV Treatment		Hours	2500
Anti-fungal		Level	0
Temperature Resistance	BS 3424 Method		-30°C /+70°C
Flame Retardant (optional)	B1,B2,M2,NFPA-701,ASTM E84,EN13501		
Lacquering (optional)	PVDF, Acrylic		
Application	Tents		

These indicated technical data are based on average results. actual data 's tolerance +-5%.Due to production procedures slight deviations can occur.All technical data are in accordance with the present standard of knowledge and give product information without legal binding.All data apply to new products

COMPANY: ZHEJIANG JINDA MEMBRANE TECHNOLOGY CO.,LTD.
 ADD: NO.51 HONGQI ROAD,MAQIAO,HAINING,ZHEJIANG.CHINA. 314413